

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 824 092 A1

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:

18.02.1998 Bulletin 1998/08

(51) Int Cl.⁶: **C04B 12/02, C04B 35/63**

(21) Application number: **97305749.0**

(22) Date of filing: **30.07.1997**

(84) Designated Contracting States:

**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**

Designated Extension States:

AL LT LV RO SI

(30) Priority: **13.08.1996 GB 9617010**

(71) Applicant: **Shaw, Richard Dudley**

Downe Orpington Kent BR6 7JN (GB)

(72) Inventor: **Shaw, Richard Dudley**

Downe Orpington Kent BR6 7JN (GB)

(74) Representative: **Crump, Julian Richard John**

F.J. Cleveland & Company

40-43 Chancery Lane

London WC2A 1JQ (GB)

(54) **Refractory binder**

(57) The present invention relates to a refractory binder that comprises a mixture of aqueous phosphate and silica sol. The silica sol has been found to gel and set in a surprisingly effective and useful way. Preferably, the refractory binder further incorporates a small

amount of magnesia as an accelerator. The present invention also provides a method of binding a refractory material such, for example, as alumina, zirconia mullite or aluminium silicate by using a refractory binder according to the invention.

EP 0 824 092 A1

Description

The present invention relates to a refractory binder. The present invention also embraces a method of binding refractory material using the binder of the present invention.

The use of ethyl silicate as a foundry or refractory binder becomes less attractive with time, on the grounds of cost and the increasing difficulty of meeting the health and safety requirements imposed upon its use.

A candidate for an alternative is a silica sol which is water based as opposed to alcohol based. Silica sol is a colloidal suspension, typically slightly alkali, p.H. c. 7.8, of amorphous silica particles in water. By various expedients known in the refractory art it can be converted to a hydrated silica gel which can be induced to set into a green shape. Indeed silica sol is used extensively in the foundry industry particularly in lost wax shell processes of precision casting. However, this relies upon a removal and drying out of water in order to achieve a green strength. This takes some time and is not amenable to proprietary processes such as the "Shaw Process" and the "Zirconal Process" which call for a fast controllable setting time of a "green" moulding or refractory. Silica sols can indeed set under certain conditions but the green strength is low until some drying has taken place.

Phosphates are well recognised also as good refractory binders. The best known being acidic such as aluminium phosphate or indeed phosphoric acid. This acidity imposes limitations on their use especially in precision pieces or basic refractories. The use of neutral ammonium phosphates has been proposed, and I have a European patent on this, EP-B-0501662. The chemical sequence in the patent is:

Polyammonium phosphate + reactive basic magnesium refractory \rightarrow magnesium phosphate gel + NH_3 , and then on heating magnesium phosphate + alumina \rightarrow aluminium/magnesium spinel + " P_2O_5 "

By " P_2O_5 " here is meant phosphate generally, and not necessarily phosphorus pentoxide. The stoichiometric content of materials disclosed herein is calculated on the basis of units of " P_2O_5 " for simplicity.

According to the present invention there is provided a refractory binder comprising a mixture of silica sol and an aqueous phosphate.

In a different aspect, the invention comprehends a method of binding a refractory material comprising mixing said refractory material with a refractory binder in accordance with the present invention, and thereafter allowing said refractory binder to gel, so as to form a green shape.

I have discovered that in a mixed binder based on a phosphate and a silica sol, the silica sol gels and sets in a surprisingly effective and useful way. Preferably the phosphate is polyammonium phosphate, and for reasons which will appear hereinafter, I particularly prefer to use the neutral polyammonium phosphate/magnesia system referred to above.

Under the appropriate conditions other phosphates can be used - acid in nature. It may be necessary to acidify the silica sol and the resultant solution may be limited in its stability. Nonetheless on an occasion when the evolution of ammonia is undesirable, an aluminium orthophosphate or phosphoric acid or magnesium phosphate, or indeed a mixture of several such phosphates, may be used as the source of gelling phosphate.

It can be demonstrated that certain sodium phosphates, potassium phosphates and insoluble phosphates can be used, but for the most part they generate many undesirable low melting point compounds detrimental to refractory properties.

A further possibility to the invention is to use a solid component for either the phosphate or the silica. That is to say, for example, mono-ammonium phosphate crystalline powder or di-ammonium phosphate or polyammonium phosphate mixed into the ceramic mixture and then the silica of the systems is provided by silica sol, or alternatively polyammonium phosphate liquid and silica fume premixed into the ceramic. There are cases where these procedures are appropriate.

The ratio of polyammonium phosphate to silica sol can be varied over a substantial range of mixtures, for example 1 phosphate to 20 sol v/v to 1 to 1 v/v, even phosphate rich up to 3 vols. of phosphate. Typical ratios for use are between 1:3 and 1:2 v/v for versatility in either refractories or foundry applications, although it has been found that the optimum (faster setting time) may be achieved at a ratio of 1 part phosphate to 8 parts of silica sol by volume.

In accordance with the invention an ammonium phosphate in the presence of silica sol may cause the silica sol to gel. The phosphate may also gel to provide, in effect, a hybrid or co-gel. The polyammonium phosphates of my patented system are referred to as P8 and I will use this nomenclature. Indeed surprisingly the strength of the gel and the rate of increase in strength are superior to any previously cited examples discovered in the literature. An addition of 10% vol. P8 to silica sol will cause a gel in 25 minutes.

With aluminium silicate refractories the presence of magnesia is considered undesirable since low melting point

compounds of magnesium silicate are formed. However, commercially many refractories and ceramics contain modest quantities of magnesia in aluminium silicates and silica in basic refractories without undue detriment to the properties. In the present invention the magnesia and alumina silicate may coexist effectively as will appear below.

For faster setting, an addition of magnesia will result in the formation of an intermediate gel of magnesium phosphate. Light magnesia or magnesium hydroxide at an addition of less than 0.5% wt of refractory or ceramic mixtures can gel the bonds very quickly. Typically a gel will form in 7 - 10 minutes at 0.1% or less depending upon the particle size of the magnesia. Thus in an alumina silicate one is considering the addition of normally 0.1% to say 0.5% of magnesia which is negligible for many applications.

A preferred mixture would be 1 volume P8 to 2 volumes silica sol 40% wt. The solution would contain 12% wt "P₂O₅" (26% wt sol). Magnesia is added to the solution or the refractory dry mixture, and a reactive alumina would be added to convert the silica sol to mullite and the magnesium phosphate to spinel upon firing. For example, the above solution could be used at 80 ccs per kilo of ceramic (a fairly typical quantity of approximately 10% wt liquid and being 5.6% H₂O). Thus, 1.2% "P₂O₅" would require about 2.4% Al₂O₃; and 2.6% SiO₂ sol would require about 5.2% Al₂O₃; i.e. making a total of about 7.6% Al₂O₃ in reactive and free form to encourage the compound formation upon firing.

Clearly a 30% wt sol could be used, or a 50% wt sol. Typically a 50% wt sol requires a particle size of 25 to 30μ to remain stable in solution as opposed to a 40% wt sol that may require a 20μ particle size, or a 30% wt sol at 10 to 15μ. In a sense the bigger the particle the less time it will take to gel, despite the fact that as a sol on its own the solution is more stable.

Similarly the polyammonium phosphate P8 is more stable than mono- or di-ammonium phosphate and thus the simpler phosphates give faster setting for less MgO. However, the dilution effect may be counter productive. The preferred ammonium phosphate is thus P8.

Thus having achieved fast controlled green set the refractory piece is held together initially by a small % of magnesium phosphate and partially gelled silica sol. With drying, the silica sol becomes increasingly significant until upon firing at 850° - 1050°C it is the predominant bond in the ceramic.

Following is a description by way of example only of methods of performing the present invention.

Example 1

A mixture of 1 volume Clinochem P8 at 50% wt polyammonium phosphate (36% "P₂O₅") is mixed with 4 volumes of 40% wt silica sol, the mixture is then mixed with tabular alumina grains and powders such as are readily known to users and manufacturers of ceramics at between 60 ccs per kilogram to 80 ccs per kilo, (depending upon the application) and then placed in a mould. At normal working temperatures, 15° - 21°C, gelation occurs in approximately 30 minutes and can be removed within one hour. No accelerator in the form of a finely divided grain is used in this example; it appears that the silica sol causes the phosphate to gel as well as vice versa.

Example 2

The same mixture, if Mg(OH)₂ is added at 0.1% wt, will set in approximately 10 minutes, and at 0.2% wt Mg(OH)₂ will set in approximately 5 minutes, depending upon temperature.

Example 3

A lightly calcined MgO - for example Lycal - if added at 0.25% wt will cause a set in 7 minutes and at 0.5% wt will cause a set in approximately 3 minutes. Longer setting times can be achieved by reducing the MgO but naturally not beyond the 30 minutes cited in Example 1.

The accelerated gelation of the system using MgO cited in Example 3 is achieved with the very modest addition of 0.25% wt lycal. In order to disperse this satisfactorily and quickly it can be mixed first with water to a thin milk of magnesia cream and added with the binder at the point of mixing. Greater reactivity and faster setting may be achieved by addition of light magnesia or magnesium hydroxide.

Example 4

To a mixture of zirconia mullite blended to give generally good packing density is added:-
a solution of

1 volume P8

3 volumes of 40% wt silica sol gelled using 0.25% wt calcined -200 mesh magnesia to total zirconia mullite body.

The mixture of solid to liquid being 1kg of refractory mixture to 65 ccs of liquid total.

This mixture when thoroughly blended then vibration cast in standard bricks gave typically the following result after firing to 1450°C

5 % Porosity 19.9
BD gm/cc 2.97
Modulus of R 11.89
Cold Crush 70.2

10 Example 5

To a mixture as Example 4 is added:-

15 1 volume P61 (a solution of sodium phosphate 40% wt)
3 volumes of silica sol 40 gelled in approximately 15 minutes and was stripped in 40 minutes using 65 ccs per kilo of liquid per kilo of refractory.

Example 6

20 To a mixture of zirconia-mullite as per Example 4 is added:-

1 volume H₂O
2 volume silica sol 40
1 volume P8

25 This provides a 20% wt silica solution.

Example 7

30 To a mixture of zirconia mullite as per Example 4 is added:-

1 volume H₂O
2 volumes silica sol
1 volume P61

35 Example 8

Example 4 was repeated, but before adding to the refractory mix, the mixture of liquids was prepared by adding to 1 volume of 40% wt aluminium orthophosphate solution, 3 volumes of silica sol 40% wt solution and stirring vigorously.

40 Example 9

To a zirconia mullite mix as described in Example 4 was added:-

45 silica sol 30 - 3 parts by volume
P8 1 part by volume

giving a 20% wt silica solution.

50 Example 10

A refractory mixture suitable as a foundry Shaw mix was prepared comprising:-

55 4 parts of wgt. -14+8 mesh Molochite - (calcined china clay)
3 parts zircon flour
1 parts calcined magnesite -200 mesh
1 part -200 mesh Malochite.

To this mix was added a solution comprising:-

2 parts silica sol 30% by weight
1 part P8

at a total liquid of 120 ccs per kilogram. In addition fibre was added at 0.75% by wgt of refractory (polypropylene fibres 5mm long x 15-20 denier).

This mixture was vigorously stirred and poured into a suitable mould where it set after approximately 90 seconds.

Example 11

Example 10 was repeated using a solution comprising:-

2 volumes of silica sol
1 volume of P61.

Example 12

Example 10 was repeated using a solution comprising:-

2 volumes of silica sol 30% wt
1 volume of P67 (a mixture of sodium phosphate and potassium phosphate).

This mixture set in approximately 120 seconds.

Example 13

Example 10 was repeated using a solution comprising:-

2 volumes of silica sol 30% wt
1 volume P7 (monopotassium phosphate 30% wt solution)
Set in 3 minutes.

It has also been found, when using ammonium polyphosphates with sols, that the resultant co-gels may be used as a means of enhancing the properties of hydraulic refractory cements. Most refractory cement bodies and particularly low cement castables have additions of silica or silicon or aluminium or phosphates or a combination of these. The use of P8 and sol very conveniently provides these additions. Furthermore the use of the co-gel may provide a means of very controlled setting times and extraordinarily high green strengths.

The refractory binders of the present invention may also be employed in the manufacture of a "Shaw Process" precision casting mould.

The co-gels may be used as fast-setting cement castables, particularly cement castables having an ultra-low cement content, typically less than 5% wt alumina cement.

Claims

1. A refractory binder comprising a mixture of silica sol and an aqueous phosphate.
2. A refractory binder as claimed in claim 1, wherein a silica sol to phosphate is in the range 20:1 to 1:3 by volume.
3. A refractory binder as claimed in claim 1 or claim 2, wherein the ratio of silica sol to phosphate is in the range 8:1 to 2:1 by volume.
4. A refractory binder as claimed in claim 1, claim 2 or claim 3, further comprising magnesia.
5. A refractory binder as claimed in claim 4, wherein the binder comprises about 0.1 to 0.5% wt magnesia.
6. A refractory binder as claimed in any preceding claim, wherein said aqueous phosphate comprises one or more

EP 0 824 092 A1

selected from phosphoric acid, aluminium orthophosphate, magnesium monophosphate, mono- or disodium phosphate, mono- or di-potassium phosphate, or insoluble phosphate, e.g dicalcium phosphate.

- 5 7. A refractory binder as claimed in any of claims 1 to 5, wherein said aqueous phosphate comprises polyammonium phosphate or ammonium phosphate.
8. A refractory binder as claimed in any preceding claim, wherein said silica sol comprises 10 to 15% wt SiO_2 .
- 10 9. A refractory binder as claimed in any preceding claim, further comprising a reactive alumina, particularly alumina sol.
10. A method of binding a refractory material comprising mixing said refractory material with a refractory binder as claimed in any of claims 1 to 9, and thereafter allowing said refractory binder to gel, so as to form a green shape.
- 15 11. A method as claimed in claim 10, wherein said refractory material is selected from alumina, aluminium silicate and zirconia mullite.
12. A method as claimed in claim 10 or claim 11, wherein the quantity of binder used is 50 to 150, preferably 60 to 80, ccs per kilogram of refractory material.
- 20 13. A fast setting cement comprising a refractory binder as claimed in any of claims 1 to 9 which has been allowed to form a co-gel of phosphate and silica gel.



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 97 30 5749

| DOCUMENTS CONSIDERED TO BE RELEVANT | | | |
|---|--|--|--|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int.CI.6) |
| X | US 4 212 680 A (NALCO CHEMICAL CO.) * the whole document * | 1-13 | C04B12/02 C04B35/63 |
| X | US 4 769 074 A (ZYP COATINGS, INC.) * column 2, line 46 - column 3, line 4 * * column 5, line 55 - column 6, line 37; claims 1-5; table 1 * | 1-13 | |
| X | US 4 591 385 A (AREMCO PRODUCTS, INC.) * the whole document * | 1-13 | |
| | | | TECHNICAL FIELDS SEARCHED (Int.CI.6) |
| | | | C04B |
| The present search report has been drawn up for all claims | | | |
| Place of search THE HAGUE | | Date of completion of the search 13 November 1997 | Examiner Luethe, H |
| <p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons S : member of the same patent family, corresponding document</p> | | | |

EPO FORM 1503 03/92 (PC/C01)